

TEST REPORT SUMMARY | Danpalon[®] Seamless Systems



DESCRIPTION	TEST STANDARD	RESULTS
Self-Ignition Temperature	ASTM D1929	> 650 °F
Rate of Burn and/or Extent	ASTM D635	CC1 Rating; <1in/min
Density of Smoke	ASTM D2843	< 75%
Surface Burning Characteristics	ASTM E84	Class A Rating: Flame Spread; 0-25 Smoke Developed Index; 0-450
Structural Performance	ASTM E330	Up to +230psf / - 90psf
Concentrated Load	-	800lb – no damage



FACADE



CLADDING



SKYLIGHT



OUTDOOR



SHADING



INTERIOR