

TEST REPORT SUMMARY | NM



DESCRIPTION	TEST STANDARD	RESULTS
Self-Ignition Temperature	ASTM D1929	> 650 °F
Rate of Burn and/or Extent	ASTM D635	CC1 Rating; <1in/min
Density of Smoke	ASTM D2843	< 75%
Surface Burning Characteristics	ASTM E84	Class A Rating: Flame Spread; 0-25 Smoke Developed Index; 0-450
Air Infiltration	ASTM E283	Pass @ 6.27psf
Water Penetration	ASTM E331	Pass @ 12psf
Structural Performance	ASTM E330	Up to +110psf / -130psf



FACADE



CLADDING



SKYLIGHT



OUTDOOR



SHADING



INTERIOR